

B A R R E

TONDE

in acciaio inossidabile, laminate o trafilate - Inox AISI 303/304/316/410/420

Dim. mm	Peso teorico Kg/m	Dim. mm	Peso teorico Kg/m
3	0,060	85	44,52
4	0,100	90	49,94
5	0,150	95	55,64
6	0,220	100	61,65
7	0,330	105	67,97
8	0,395	110	74,60
10	0,616	115	81,54
12	0,888	120	88,78
14	1,208	125	96,33
15	1,387	130	104,20
16	1,578	135	112,40
18	1,998	140	120,80
20	2,466	145	129,60
22	2,984	150	138,70
24	3,551	155	148,10
25	3,853	160	157,80
26	4,168	165	167,90
28	4,834	170	178,20
30	5,549	175	188,80
32	6,313	180	199,80
35	7,552	185	211,00
38	8,903	190	222,60
40	9,864	200	246,60
42	10,880	225	312,00
45	12,480	250	385,30
48	14,200	275	466,30
50	15,410	300	554,90
52	16,700	325	651,20
55	18,650	350	755,20
60	22,220		
62	23,700		
65	26,050		
70	30,210		
75	34,680		
80	39,460		

ANGOLARI

in acciaio inossidabile, laminate a caldo, ricotte e decapate - Inox AISI 304/316

Dim. mm	Peso teorico Kg/m	Dim. mm	Peso teorico Kg/m
20/20/3	0,880	40/40/5	2,950
20/20/4	1,130	50/50/5	3,770
25/25/3	1,120	50/50/6	4,480
25/25/4	1,540	60/60/6	5,520
30/30/3	1,360	80/80/8	9,660
30/30/4	1,780	100/100/10	15,100
40/40/4	2,420		