

TUBO SENZA SALDATURA

in acciaio inossidabile per impianti ad alta temperatura o corrosione generale
Tolleranze secondo norma ANSI B36.10 - B36.19 - BS1600

TONDO - Inox AISI 304/316 (Peso teorico)

DN	D-est.	D-est.	SCHED. 5S		SCHED. 10S	
Diam. Nom.	Pollici	mm	Sp.	Kg/m	Sp.	Kg/m
6	1/8	10,24	/	/	1,24	0,29
8	1/4	13,72	/	/	1,65	0,50
10	3/8	17,15	/	/	1,65	0,63
15	1/2	21,34	1,65	0,82	2,11	1,02
20	3/4	26,70	1,65	1,05	2,11	1,31
25	1	33,40	1,65	1,32	2,77	2,12
32	1-1/4	42,16	1,65	1,68	2,77	2,74
40	1-1/2	48,26	1,65	1,94	2,77	3,17
50	2	60,30	1,65	2,45	2,77	4,01
65	2-1/2	73,03	2,11	3,76	3,05	5,36
80	3	88,90	2,11	4,60	3,05	6,57
90	3-1/2	101,6	2,11	5,28	3,05	7,54
100	4	114,3	2,11	5,95	3,05	8,52
125	5	141,3	2,77	9,65	3,40	11,79
150	6	168,3	2,77	11,54	3,40	14,10
200	8	219,1	2,77	15,07	3,76	20,34
250	10	273,0	3,40	23,05	4,19	28,31
300	12	323,9	3,96	31,84	4,57	36,68

DN	D-est.	D-est.	SCHED. 40S		SCHED. 80S	
Diam. Nom.	Pollici	mm	Sp.	Kg/m	Sp.	Kg/m
6	1/8	10,24	1,73	0,37	2,41	0,47
8	1/4	13,72	2,24	0,64	3,02	0,82
10	3/8	17,15	2,31	0,87	3,20	1,12
15	1/2	21,34	2,77	1,29	3,73	1,65
20	3/4	26,70	2,87	1,71	3,91	2,23
25	1	33,40	3,38	2,55	4,55	3,29
32	1-1/4	42,16	3,56	3,45	4,85	4,55
40	1-1/2	48,26	3,68	4,13	5,08	5,51
50	2	60,30	3,91	5,54	5,54	7,62
65	2-1/2	73,03	5,16	8,79	7,01	11,63
80	3	88,90	5,49	11,51	7,62	15,56
90	3-1/2	101,6	5,74	13,83	8,08	18,99
100	4	114,3	6,02	16,38	8,56	22,74
125	5	141,3	6,55	22,20	9,52	31,54
150	6	168,3	7,11	28,79	10,97	43,37
200	8	219,1	8,18	43,34	12,70	65,86
250	10	273,0	9,27	61,44	12,70	83,00
300	12	323,9	9,52	75,24	12,70	99,31

Per le misure e/o spessori non a catalogo chiedere
al nostro ufficio commerciale.